

Table 2 Absorption of CEB (10% w/v) in veneer and solid wood of rubber wood

CEB (10%w/v) concentration (%)	*Mean absorption in rubber wood (kg/m <sup>3</sup> )
2.5	2.39
3	3.28
5	3.36